

# Online Research @ Cardiff

This is an Open Access document downloaded from ORCA, Cardiff University's institutional repository: <https://orca.cardiff.ac.uk/id/eprint/93741/>

This is the author's version of a work that was submitted to / accepted for publication.

Citation for final published version:

Crole, David Alexander, Freakley, Simon J., Edwards, Jennifer Kelly ORCID: <https://orcid.org/0000-0003-4089-2827> and Hutchings, Graham John ORCID: <https://orcid.org/0000-0001-8885-1560> 2016. Direct synthesis of hydrogen peroxide in water at ambient temperature. Proceedings of the Royal Society A: Mathematical, Physical and Engineering Sciences 472 (2190) , 20160156. 10.1098/rspa.2016.0156 file

Publishers page: <http://dx.doi.org/10.1098/rspa.2016.0156>  
<<http://dx.doi.org/10.1098/rspa.2016.0156>>

Please note:

Changes made as a result of publishing processes such as copy-editing, formatting and page numbers may not be reflected in this version. For the definitive version of this publication, please refer to the published source. You are advised to consult the publisher's version if you wish to cite this paper.

This version is being made available in accordance with publisher policies.

See

<http://orca.cf.ac.uk/policies.html> for usage policies. Copyright and moral rights for publications made available in ORCA are retained by the copyright holders.



---

# Direct synthesis of hydrogen peroxide in water at ambient temperature

David A. Crole, Simon J. Freakley, Jennifer K. Edwards and Graham J. Hutchings\*

*Cardiff Catalysis Institute and School of Chemistry, Main Building, Park Place, Cardiff, CF10 3AT, UK*

**Keywords:** Hydrogen peroxide; gold; palladium; green chemistry

---

## Summary

The direct synthesis of hydrogen peroxide from hydrogen and oxygen has been studied using an Au-Pd/TiO<sub>2</sub> catalyst. The aim of this work is to understand the balance of synthesis and sequential degradation reactions using an aqueous, stabiliser-free solvent at ambient temperature. The effects of the reaction conditions on the productivity of hydrogen peroxide formation and the undesirable hydrogenation and decomposition reactions are investigated. Reaction temperature, solvent composition and reaction time have been studied and indicate that when using water as the solvent the hydrogen peroxide decomposition reaction is the predominant degradation pathway, which provides new challenges for catalyst design which has previously focused on minimising the subsequent hydrogenation reaction. This is of importance for the application of this catalytic approach for water purification.

## Introduction

Hydrogen peroxide (H<sub>2</sub>O<sub>2</sub>) is a significant commodity chemical with an annual usage now exceeding 3 million tonnes per annum and increasing(1). H<sub>2</sub>O<sub>2</sub> is used in a number of selective oxidation processes, such as the synthesis of propene oxide from propene and H<sub>2</sub>O<sub>2</sub>(2), and also non-synthetic applications which make use of its oxidative properties such as cleaning and bleaching. The existing indirect anthraquinone process for producing H<sub>2</sub>O<sub>2</sub> is highly optimised to give high H<sub>2</sub> selectivity towards H<sub>2</sub>O<sub>2</sub>, however, it only proves to be economically viable when operated at a large scale, typically 10<sup>5</sup> tons/annum, and hence production currently has to be centralised. Due to this, H<sub>2</sub>O<sub>2</sub> is transported to the point of use in a high concentration aqueous solution with added stabilisers, necessitating dilution and potentially removal of stabilisers for it to be effective for many uses, particularly bleaching applications when it is used in very dilute form (3-8 vol%)(3).

The ability to produce H<sub>2</sub>O<sub>2</sub> at a desired concentration at the point of use could prove to be a green and economical process. This could potentially be achieved via the direct synthesis of H<sub>2</sub>O<sub>2</sub> from oxygen and hydrogen to localise the supply of H<sub>2</sub>O<sub>2</sub>. Whilst a conceptual simple reaction unfortunately the formation of water is thermodynamically preferred and so the design of the catalyst for the synthesis reaction is of prime importance. Monometallic Pd catalysts have been extensively studied for this reaction(3-5), however, these catalysts can hydrogenate H<sub>2</sub>O<sub>2</sub> if no acid or halide stabilisers are present. Hutchings and co-workers found that Au-Pd catalysts are selective and productive, even in the absence of promoters such as acid and halides(6).

---

\*Author for correspondence (Hutch@cardiff.ac.uk).

†Present address: Cardiff Catalysis Institute and School of Chemistry, Main Building, Park Place, Cardiff, CF10 3AT, UK

Various solvents, generally consisting of water and/or alcohols, in combination with acid and/or halide promoters, have been used for the heterogeneously catalysed direct synthesis of  $\text{H}_2\text{O}_2$ . We have extensively reported experiments using a methanol and water mixture in an approximate 2:1 ratio, generally in the absence of acid or halides([1](#), [6](#), [7](#)). Lunsford and co-workers utilised a water or ethanol solvent with the addition of chloride, bromide, hydrochloric acid and sulphuric acid promoters([8-11](#)). Choudhary and co-workers utilise an acidic aqueous medium (sulphuric or phosphoric acid), in most cases with one or more halide promoter([12-21](#)). Park and co-workers use a solution of methanol with dissolved NaBr([22-32](#)). Biasi and co-workers generally use methanol in the absence of promoters([33-39](#)), but have also used acidified, bromide-promoted aqueous solutions([40](#)). There are, however, limited studies on the aqueous direct synthesis of  $\text{H}_2\text{O}_2$  in the absence of promoters.

If the generation of  $\text{H}_2\text{O}_2$  in aqueous solution without additives becomes viable, it would negate the necessity for the extraction of synthesised  $\text{H}_2\text{O}_2$  from the anthraquinone process solvents. Furthermore, the removal of stabilisers (as with anthraquinone process produced  $\text{H}_2\text{O}_2$ ) or promoters (as may be necessary for  $\text{H}_2\text{O}_2$  produced by acid or halide promoted direct synthesis) would not be required. The ability to efficiently generate  $\text{H}_2\text{O}_2$  in a water stream also presents opportunities for water cleaning technologies to be developed. It is this latter application for which there is considerable current interest as  $\text{H}_2\text{O}_2$  could then have the potential to replace chlorine as a disinfectant for water which would only be possible if stabiliser-free  $\text{H}_2\text{O}_2$  can be produced in water.

In this work, we examine the effect on the productivity and hydrogenation/decomposition rates of a 2.5% Au 2.5% Pd /  $\text{TiO}_2$  catalyst when reaction conditions are moved towards the use of water as a solvent and room temperature reactions. These conditions present a more environmentally friendly and economical reaction compared to previously used conditions([6](#)) as there are no energy demands for heating or cooling and the  $\text{H}_2\text{O}_2$  requires no further extraction/purification. Using this study to help understand the effect of changing reaction parameters on all processes associated with the direct synthesis of  $\text{H}_2\text{O}_2$  and identify challenges therein will allow for rational design of catalysts for optimal function in an aqueous / ambient temperature reaction condition.

## Experimental

### Catalyst preparation

The 2.5 wt% Au-2.5 wt% Pd/ $\text{TiO}_2$  catalyst was prepared by wet impregnation of  $\text{TiO}_2$  (Degussa, Aeroxide P25). A solution of  $\text{HAuCl}_4 \cdot 3\text{H}_2\text{O}$  (1.25 ml, 10g Au/ml, Johnson Matthey), solid  $\text{PdCl}_2$  (0.0208 g, Johnson Matthey) and de-ionised water (1 ml) were combined and stirred at 80 °C until the  $\text{PdCl}_2$  was completely dissolved. At this point  $\text{TiO}_2$  (0.475 g) was added and the mixture continuously stirred and heated until a thick paste was formed. The paste was dried in an oven (110 °C, 16 h), ground to a fine powder and calcined under static air (400 °C, 3 h, 20 °C  $\text{min}^{-1}$ ).

### $\text{H}_2\text{O}_2$ synthesis, decomposition and hydrogenation

$\text{H}_2\text{O}_2$  synthesis, hydrogenation and decomposition experiments were evaluated using a Parr Instruments stainless steel autoclave with a volume of either 100 ml or 50 ml and a maximum working pressure of 14 MPa. To evaluate  $\text{H}_2\text{O}_2$  synthesis the following reaction conditions were used. The autoclave was charged with catalyst (0.010 g) and solvent (8.5 g HPLC grade  $\text{H}_2\text{O}$  and/or HPLC grade methanol, Fischer Scientific) and sealed. The autoclave was then purged three times with 5%  $\text{H}_2/\text{CO}_2$  before filling with 5%  $\text{H}_2/\text{CO}_2$  to a pressure of 2.9 MPa (420 psi) followed by the addition of a further 1.1MPa (160 psi) 25%  $\text{O}_2/\text{CO}_2$  (both BOC speciality gasses). The reaction mixture was stirred at 1200 rpm at systematically varied reaction times and temperatures.  $\text{H}_2\text{O}_2$  yield was determined by titrating aliquots of the filtered post-reaction solution with acidified  $\text{Ce}(\text{SO}_4)_2$  solution (c.a. 0.01 M, Sigma Aldrich) in the presence of Ferroin indicator (c.a. 0.1 ml, Sigma Aldrich).

$\text{H}_2\text{O}_2$  hydrogenation and decomposition experiments were carried out with a similar procedure to that of  $\text{H}_2\text{O}_2$  synthesis experiments but only 420 psi (2.9 MPa) 5%  $\text{H}_2/\text{CO}_2$  or 420 psi (2.9 MPa) 25%  $\text{O}_2/\text{CO}_2$  were added to the reactor, respectively. Furthermore, a reaction solvent containing 4 wt%  $\text{H}_2\text{O}_2$ , prepared by the addition of  $\text{H}_2\text{O}_2$  solution (50 wt%, 0.68 g, Sigma Aldrich) to  $\text{H}_2\text{O}$  (7.82 g), was used. The concentration of  $\text{H}_2\text{O}_2$  in the reaction solution was accurately

determined before and after the reaction by titrating aliquots of the reaction solution with acidified  $\text{Ce}(\text{SO}_4)_2$  in the presence of Ferroin indicator. When a hydrogenation experiment is performed, the measured degree of  $\text{H}_2\text{O}_2$  degradation represents the sum of both hydrogenation and decomposition processes; thus net hydrogenation can be determined by subtracting the measured decomposition value from the measured total hydrogenation/degradation value, assuming that the reactions happen independently of each other. Aside from the noted differences, reaction parameters are identical to those used for synthesis reactions.

## Results and Discussion

In our previous studies on the direct synthesis of  $\text{H}_2\text{O}_2$ ,<sup>(4, 6, 41)</sup> reaction conditions have been standardised to allow differences in  $\text{H}_2\text{O}_2$  yield to solely reflect differences in catalyst performance. The reaction parameters in these experiments were a 2.9 g  $\text{H}_2\text{O}$ /5.6 g methanol solvent mixture, temperature of 2 °C and a reaction duration of 30 min (gas compositions and pressures identical to those reported in the experimental procedure).<sup>(6)</sup> In this work, conditions for the direct synthesis of  $\text{H}_2\text{O}_2$  are investigated at a range of temperatures and solvent compositions with the aim of understanding how the reaction system affects the balance of  $\text{H}_2\text{O}_2$  synthesis versus the sequential degradation pathways.

Time on line studies were carried out in the previously utilised  $\text{H}_2\text{O}$ /methanol solvent mixture in addition to  $\text{H}_2\text{O}$  and methanol solvents. Productivity values are reported in figure 1a and show that in each system the productivity is highest at short reaction times as expected when the  $\text{H}_2$  concentration will be highest and also the rates of  $\text{H}_2\text{O}_2$  degradation will be minimal due to the low concentrations of  $\text{H}_2\text{O}_2$  in the reaction mixtures. Comparing the solvent compositions it is clear to see that the productivity is highest when methanol is used and lowest when  $\text{H}_2\text{O}$  is used across the reaction times investigated. Using Henry's law to compare the solubility of hydrogen in the three solvent compositions shows that hydrogen solubility is around an order of magnitude higher in methanol compared to  $\text{H}_2\text{O}$ , with Henry's constant ( $H^{\text{sp}}$ ) values at 20°C of  $9.34 \times 10^{-3} \text{ mol atm}^{-1} \text{ L}^{-1}$  and  $8.04 \times 10^{-4} \text{ mol atm}^{-1} \text{ L}^{-1}$  respectively. The amount in ppm of  $\text{H}_2\text{O}_2$  present in each reaction is shown in figure 1b. We observed that almost all of the  $\text{H}_2\text{O}_2$  synthesised in the methanol solvent is produced in the first 5 min, whereas in  $\text{H}_2\text{O}$  the maximum  $\text{H}_2\text{O}_2$  concentration is only attained after 40 min reaction. These observations indicate that the performance of the catalyst in the different solvent compositions is likely to be governed by gas solubility and mass transport effects. The effect of gas solubility can also control the balance of the synthesis / hydrogenation / decomposition pathways in the direct synthesis process shown in scheme 1.

The hydrogenation and decomposition reactions of the different solvent compositions were also studied in an analogous manner using the same catalyst. For the decomposition reaction, figure 2a, it was observed that the relationship between the amounts of  $\text{H}_2\text{O}_2$  decomposed and time is close to linear for all solvent compositions. It was observed that the least decomposition occurs in the methanol solvent, followed by the  $\text{H}_2\text{O}$ /methanol solvent and the greatest decomposition occurring in the  $\text{H}_2\text{O}$  solvent. These reactions were conducted without the presence of  $\text{H}_2$  in the autoclave which indicates the low decomposition rate observed in the methanol solvent is not a result of competitive hydrogenation reactions and in fact  $\text{H}_2\text{O}_2$  is stabilised in the methanol solvent with respect to the water solvent.

For sequential hydrogenation, figure 2b, we see an inverse of the trend seen for decomposition, with the lowest extent of hydrogenation with respect to time in a  $\text{H}_2\text{O}$  solvent where  $\text{H}_2$  solubility will be limited compared to alcohol containing solvent compositions. Methanol and  $\text{H}_2\text{O}$ /methanol solvents appear to have very similar initial rates of hydrogenation, indicating that the addition of 66% methanol to  $\text{H}_2\text{O}$  reduces the mass transport limitations and the catalyst is likely operating in the kinetic regime. The plots for hydrogenation activity tend to plateau at long reaction times; this indicates that after an extended reaction the extent of hydrogenation becomes limited by the availability of hydrogen in solution. These observations indicate that when changing the reaction conditions for the direct synthesis, additional considerations need to be made in terms of catalyst design. If direct synthesis of  $\text{H}_2\text{O}_2$  is to be successfully achieved in water as solvent, suppressing the decomposition reaction becomes an important factor in catalyst design, not only the suppression of the sequential hydrogenation, as has been the focus of all previous research.

Figure 3 shows an extended study of the solvent effects on the three competing reactions. We observe a maximum measured productivity of  $\text{H}_2\text{O}_2$  during a 30 min reaction in the 34%  $\text{H}_2\text{O}$  solvent, this is the solvent ratio which has previously been found to be optimal for the Au-Pd /  $\text{TiO}_2$  catalyst when tested at 2 °C. Increasing the methanol content of the solvent past this point has little effect on the observed productivity, however it increases the rate of  $\text{H}_2\text{O}_2$  hydrogenation due to the increased  $\text{H}_2$  solubility. The observation that the net  $\text{H}_2\text{O}_2$  produced remains somewhat constant suggests the fact that the synthesis reaction also increases in proportion to the increased  $\text{H}_2$  solubility. These results again highlight the need to design catalysts with reaction conditions in mind. In  $\text{H}_2\text{O}$  rich solvent compositions where  $\text{H}_2$  availability is low compared to methanol rich solvent compositions, the hydrogenation and decomposition reactions occur with similar rate ( $600 \text{ mol kg}_{\text{cat}}^{-1}$



<sup>1</sup> h<sup>-1</sup> net hydrogenation vs 450 mol kg<sub>cat</sub><sup>-1</sup> h<sup>-1</sup> decomposition in an aqueous system) so catalyst design should focus on minimising both reactions equally. In methanol rich solvent compositions the synthesis activity is increased due to the higher H<sub>2</sub> availability but as a consequence so is the H<sub>2</sub>O<sub>2</sub> hydrogenation reaction. At this condition the rates of hydrogenation are much higher than the rates of decomposition (790 mol kg<sub>cat</sub><sup>-1</sup> h<sup>-1</sup> net hydrogenation vs 110 mol kg<sub>cat</sub><sup>-1</sup> h<sup>-1</sup> decomposition in a methanol system) suggesting that when working at conditions with high hydrogen availability, deconvoluting the selective and unselective hydrogen activation is most important.

H<sub>2</sub>O<sub>2</sub> synthesis productivity and the activity of the two degradation processes, decomposition and hydrogenation, at increasing temperatures are shown in figure 4. Net H<sub>2</sub>O<sub>2</sub> productivity was found to decrease significantly with increasing temperature; this is tied to the fact that we see an increase in both degradation processes with increasing temperature. At a temperature of 50 °C we observe for the first time the decomposition rate to be higher than the hydrogenation rate which could be a result of increased thermal decomposition rates of H<sub>2</sub>O<sub>2</sub>.

## Conclusions

Changing the reaction conditions for the direct synthesis of H<sub>2</sub>O<sub>2</sub> from the ‘standard’ conditions using methanol/water at 2 °C to ‘aqueous / ambient’ conditions we observe a marked decrease in H<sub>2</sub>O<sub>2</sub> yield. This is due in part to increased H<sub>2</sub>O<sub>2</sub> degradation that occurs with both an increase in reaction temperature and an increased amount of H<sub>2</sub>O in the solvent. The decreased yield is also due to a reduced rate of H<sub>2</sub>O<sub>2</sub> synthesis due the reduced H<sub>2</sub> solubility that again occurs with both an increase in temperature and an increased amount of H<sub>2</sub>O in the solvent. The concomitant positive effect of reduced H<sub>2</sub> solubility in the ‘aqueous / ambient’ conditions is that the hydrogenation of H<sub>2</sub>O<sub>2</sub> is relatively less of a concern than under ‘standard’ conditions. This means that catalysts that are highly active but somewhat unselective due to over hydrogenation under ‘standard’ conditions may prove productive under the ‘aqueous / ambient’ conditions that will be required in water purification applications. It is therefore clear that an improved catalyst design is required to synthesise hydrogen peroxide from H<sub>2</sub> and O<sub>2</sub> in water as solvent at ambient temperature. The main concern to be addressed is the catalyst activity as the catalyst needs to operate with much lower levels of dissolved H<sub>2</sub>. To achieve this we consider that catalysts with smaller active nanoparticles could provide the improvement required. In addition, changes in the catalyst formulation should be explored using compositions in which gold, which is not particularly active for the direct synthesis of hydrogen peroxide, is substituted for other components such as tin oxide. (42)

## Additional Information

### Acknowledgments

We thank Selden Research Limited for financial support for a studentship for David. A. Crole. We thank Peter Woodhead for useful discussions.

### Funding Statement

The research has been funded by Selden Research Limited and Cardiff University.

### Data Accessibility

Readers can contact [opendata@cardiff.ac.uk](mailto:opendata@cardiff.ac.uk)

### Competing Interests

The authors have no competing financial interests.

### Authors' Contributions

David A. Crole, Simon J. Freakley, Jennifer K. Edwards and Graham J. Hutchings each provided substantial contributions to conception and design, or acquisition of data, or analysis and interpretation of data, drafting the article or revising it critically for important intellectual content and final approval of the version to be published. The research was directed by Graham J. Hutchings.

## References

1. Edwards JK, Hutchings GJ. Palladium and gold-palladium catalysts for the direct synthesis of hydrogen peroxide. *Angewandte Chemie*. 2008;47(48):9192-8.
2. Blanco-Brieva G, Capel-Sanchez MC, de Frutos MP, Padilla-Polo A, Campos-Martin JM, Fierro JLG. New Two-Step Process for Propene Oxide Production (HPPO) Based on the Direct Synthesis of Hydrogen Peroxide. *Industrial & Engineering Chemistry Research*. 2008;47(21):8011-5.
3. Samanta C. Direct synthesis of hydrogen peroxide from hydrogen and oxygen: An overview of recent developments in the process. *Applied Catalysis A: General*. 2008;350(2):133-49.
4. Edwards JK, Freakley SJ, Lewis RJ, Pritchard JC, Hutchings GJ. Advances in the direct synthesis of hydrogen peroxide from hydrogen and oxygen. *Catalysis Today*. 2015;248:3-9.
5. Henkel H, Weber W. Manufacture of hydrogen peroxide. US Patent 1,108,752. 1914.
6. Edwards J, Solsona B, Landon P, Carley A, Herzing A, Kiely C, et al. Direct synthesis of hydrogen peroxide from H<sub>2</sub> and O<sub>2</sub> using TiO<sub>2</sub>-supported Au-Pd catalysts. *Journal of Catalysis*. 2005;236(1):69-79.
7. Piccinini M, Ntainjua E, Edwards JK, Carley AF, Moulijn JA, Hutchings GJ. Effect of the reaction conditions on the performance of Au-Pd/TiO<sub>2</sub> catalyst for the direct synthesis of hydrogen peroxide. *Physical chemistry chemical physics : PCCP*. 2010;12(10):2488-92.
8. Han Y, Lunsford J. Direct formation of HO from H and O over a Pd/SiO catalyst: the roles of the acid and the liquid phase. *Journal of Catalysis*. 2005;230(2):313-6.
9. Han YF, Lunsford JH. A comparison of ethanol and water as the liquid phase in the direct formation of H<sub>2</sub>O<sub>2</sub> from H<sub>2</sub> and O<sub>2</sub> over a palladium catalyst. *Catalysis Letters*. 2005;99(1-2):13-9.
10. Liu Q, Lunsford J. The roles of chloride ions in the direct formation of H<sub>2</sub>O<sub>2</sub> from H<sub>2</sub> and O<sub>2</sub> over a Pd/SiO<sub>2</sub> catalyst in a H<sub>2</sub>SO<sub>4</sub>/ethanol system. *Journal of Catalysis*. 2006;239(1):237-43.
11. Liu Q, Lunsford JH. Controlling factors in the direct formation of H<sub>2</sub>O<sub>2</sub> from H<sub>2</sub> and O<sub>2</sub> over a Pd/SiO<sub>2</sub> catalyst in ethanol. *Applied Catalysis A: General*. 2006;314(1):94-100.
12. Choudhary VR, Gaikwad AG, Sansare SD. Activation of supported Pd metal catalysts for selective oxidation of hydrogen to hydrogen peroxide. *Catalysis Letters*. 2002;83(3-4):235-9.
13. Choudhary VR, Samanta C, Gaikwad AG. Drastic increase of selectivity for H<sub>2</sub>O<sub>2</sub> formation in direct oxidation of H<sub>2</sub> to H<sub>2</sub>O<sub>2</sub> over supported Pd catalysts due to their bromination. *Chemical Communications*. 2004;10(18):2054-5.
14. Choudhary V, Samanta C. Role of chloride or bromide anions and protons for promoting the selective oxidation of H<sub>2</sub> by O<sub>2</sub> to H<sub>2</sub>O<sub>2</sub> over supported Pd catalysts in an aqueous medium. *Journal of Catalysis*. 2006;238(1):28-38.
15. Choudhary VR, Samanta C, Choudhary TV. Factors influencing decomposition of H<sub>2</sub>O<sub>2</sub> over supported Pd catalyst in aqueous medium. *Journal of Molecular Catalysis A: Chemical*. 2006;260(1-2):115-20.
16. Choudhary V, Jana P. Synergetic effect of two halogen promoters present in acidic reaction medium or catalyst on the H<sub>2</sub>O<sub>2</sub> formation (in H<sub>2</sub>-to-H<sub>2</sub>O<sub>2</sub> oxidation) and destruction over Pd/C (or Al<sub>2</sub>O<sub>3</sub>) catalyst. *Journal of Catalysis*. 2007;246(2):434-9.
17. Choudhary VR, Samanta C, Jana P. Formation from direct oxidation of H<sub>2</sub> and destruction by decomposition/hydrogenation of H<sub>2</sub>O<sub>2</sub> over Pd/C catalyst in aqueous medium containing different acids and halide anions. *Applied Catalysis A: General*. 2007;317(2):234-43.
18. Choudhary VR, Samanta C, Jana P. Hydrogenation of hydrogen peroxide over palladium/carbon in aqueous acidic medium containing different halide anions under static/flowing hydrogen. *Industrial and Engineering Chemistry Research*. 2007;46(10):3237-42.
19. Samanta C, Choudhary VR. Direct formation of H<sub>2</sub>O<sub>2</sub> from H<sub>2</sub> and O<sub>2</sub> and decomposition/hydrogenation of H<sub>2</sub>O<sub>2</sub> in aqueous acidic reaction medium over halide-containing Pd/SiO<sub>2</sub> catalytic system. *Catalysis Communications*. 2007;8(12):2222-8.
20. Samanta C, Choudhary VR. Direct oxidation of H<sub>2</sub> to H<sub>2</sub>O<sub>2</sub> over Pd/CeO<sub>2</sub> catalyst under ambient conditions: Influence of halide ions. *Chemical Engineering Journal*. 2008;136(2-3):126-32.
21. Choudhary VR, Jana P. Direct H<sub>2</sub>-to-H<sub>2</sub>O<sub>2</sub> oxidation over highly active/selective Br-F-Pd/Al<sub>2</sub>O<sub>3</sub> catalyst in aqueous acidic medium: Influence of process conditions on the H<sub>2</sub>O<sub>2</sub> formation. *Applied Catalysis A: General*. 2009;352(1-2):35-42.
22. Park S, Jung JC, Seo JG, Kim TJ, Chung Y-M, Oh S-H, et al. Direct Synthesis of Hydrogen Peroxide from Hydrogen and Oxygen Over Palladium Catalysts Supported on SO<sub>3</sub>H-Functionalized SiO<sub>2</sub> and TiO<sub>2</sub>. *Catalysis Letters*. 2009;130(3-4):604-7.
23. Park S, Kim TJ, Chung Y-M, Oh S-H, Song IK. Direct Synthesis of Hydrogen Peroxide from Hydrogen and Oxygen over Palladium Supported on SO<sub>3</sub>H-Functionalized SBA-15. *Catalysis Letters*. 2009;130(3-4):296-300.
24. Park S, Lee S, Song S, Park D, Baek S, Kim T, et al. Direct synthesis of hydrogen peroxide from hydrogen and oxygen over palladium-exchanged insoluble heteropolyacid catalysts. *Catalysis Communications*. 2009;10(4):391-4.
25. Park S, Seo JG, Jung JC, Baek S-H, Kim TJ, Chung Y-M, et al. Direct synthesis of hydrogen peroxide from hydrogen and oxygen over palladium catalysts supported on TiO<sub>2</sub>-ZrO<sub>2</sub> mixed metal oxides. *Catalysis Communications*. 2009;10(13):1762-5.
26. Park S, Baek S-H, Kim TJ, Chung Y-M, Oh S-H, Song IK. Direct synthesis of hydrogen peroxide from hydrogen and oxygen over palladium catalyst supported on SO<sub>3</sub>H-functionalized mesoporous silica. *Journal of Molecular Catalysis A: Chemical*. 2010;319(1-2):98-107.
27. Park S, Kim TJ, Chung Y-M, Oh S-H, Song IK. Direct synthesis of hydrogen peroxide from hydrogen and oxygen over insoluble Pd<sub>0.15</sub>M<sub>2.5</sub>H<sub>0.2</sub>PW<sub>12</sub>O<sub>40</sub> (M = K, Rb, and Cs) heteropolyacid catalysts. *Research on Chemical Intermediates*. 2010;36(6-7):639-46.
28. Park S, Park DR, Choi JH, Kim TJ, Chung Y-M, Oh S-H, et al. Direct synthesis of hydrogen peroxide from hydrogen and oxygen over insoluble Cs<sub>2.5</sub>H<sub>0.5</sub>PW<sub>12</sub>O<sub>40</sub> heteropolyacid supported on Pd/MCF. *Journal of Molecular Catalysis A: Chemical*. 2010;332(1-2):76-83.
29. Park S, Park DR, Choi JH, Kim TJ, Chung Y-M, Oh S-H, et al. Direct

synthesis of hydrogen peroxide from hydrogen and oxygen over palladium catalyst supported on H3PW12O40-incorporated MCF silica. *Journal of Molecular Catalysis A: Chemical*. 2011;336(1-2):78-86.

30. Park S, Choi JH, Kim TJ, Chung Y-M, Oh S-H, Song IK. Direct synthesis of H<sub>2</sub>O<sub>2</sub> from H<sub>2</sub> and O<sub>2</sub> over Pd catalyst supported on Cs<sub>2</sub>.5H<sub>0.5</sub>PW<sub>12</sub>O<sub>40</sub>-MCF silica. *Catalysis Today*. 2012;185(1):162-7.

31. Park S, Choi JH, Kim TJ, Chung Y-M, Oh S-H, Song IK. Direct synthesis of hydrogen peroxide from hydrogen and oxygen over Pd/CsXH<sub>3</sub>-XPW<sub>12</sub>O<sub>40</sub>/MCF (X=1.7, 2.0, 2.2, 2.5, and 2.7) catalysts. *Journal of Molecular Catalysis A: Chemical*. 2012;353-354:37-43.

32. Park S, Lee J, Song JH, Kim TJ, Chung Y-M, Oh S-H, et al. Direct synthesis of hydrogen peroxide from hydrogen and oxygen over Pd/HZSM-5 catalysts: Effect of Brønsted acidity. *Journal of Molecular Catalysis A: Chemical*. 2012;363-364:230-6.

33. Biasi P, Menegazzo F, Pinna F, Eränen K, Canu P, Salmi TO. Hydrogen peroxide direct synthesis: Selectivity enhancement in a trickle bed reactor.

*Industrial and Engineering Chemistry Research*. 2010;49(21):10627-32.

34. Gudarzi D, Simakova OA, Hernández Carucci JR, Biasi PD, Eränen K, Kolehmainen E, et al. Direct synthesis of H<sub>2</sub>O<sub>2</sub> from H<sub>2</sub> and O<sub>2</sub> over carbon supported Au, Pd and Au-Pd/C bimetallic catalysts. *Chemical Engineering Transactions*. 2010;21:925-30.

35. Biasi P, Zancanella S, Pinna F, Canu P, Salmi TO. Hydrogen peroxide direct synthesis: From catalyst preparation to continuous reactors. *Chemical Engineering Transactions*. 2011;24:49-54.

36. Biasi P, Canu P, Menegazzo F, Pinna F, Salmi TO. Direct Synthesis of Hydrogen Peroxide in a Trickle Bed Reactor: Comparison of Pd-Based Catalysts. *Industrial & Engineering Chemistry Research*. 2012;51(26):8883-90.

37. Gemo N, Biasi P, Canu P, Salmi TO. Mass transfer and kinetics of H<sub>2</sub>O<sub>2</sub> direct synthesis in a batch slurry reactor. *Chemical Engineering Journal*. 2012;207-208:539-51.

38. Biasi P, Menegazzo F, Canu P, Pinna F, Salmi TO. Role of a Functionalized Polymer (K2621) and an Inorganic Material (Sulphated Zirconia) as Supports in Hydrogen Peroxide Direct

Synthesis in a Continuous Reactor. *Industrial & Engineering Chemistry Research*. 2013;130916123939006.

39. Sterchele S, Biasi P, Centomo P, Canton P, Campestrini S, Salmi T, et al. Pd-Au and Pd-Pt catalysts for the direct synthesis of hydrogen peroxide in absence of selectivity enhancers. *Applied Catalysis A: General*. 2013;468:160-74.

40. Biasi P, García-Serna J, Bittante A, Salmi T. Direct synthesis of hydrogen peroxide in water in a continuous trickle bed reactor optimized to maximize productivity. *Green Chemistry*. 2013;15(9):2502.

41. Edwards JK, Solsona B, N EN, Carley AF, Herzing AA, Kiely CJ, et al. Switching off hydrogen peroxide hydrogenation in the direct synthesis process. *Science*. 2009;323(5917):1037-41.

42. Freakley SJ, He Q, Harrhy JH, Lu L, Crole DA, Morgan DJ et al., Palladium-tin catalysts for the direct synthesis of H<sub>2</sub>O<sub>2</sub> with high selectivity *Science* 2016, 351, 965-968.

## Figure and table captions

**Figure 1** – Time on line  $\text{H}_2\text{O}_2$  productivity (a) and yield (b) in water, 34% water / 66% methanol and methanol solvent systems.

■ – Methanol, ● – 34% Water / 66% Methanol, ▲ - Water.

Conditions: Reaction time as indicated, 8.5g solvent, 100 ml autoclave, ambient temperature (20-25°C), 1200rpm, 10mg catalyst, 420 psi  $\text{H}_2/\text{CO}_2$  + 160 psi  $\text{O}_2/\text{CO}_2$ .

**Figure 2** – Time on line  $\text{H}_2\text{O}_2$  decomposition (a) and net hydrogenation (b) in water, 34% water / 66% methanol and methanol solvent systems.

■ – Methanol, ● – 34% Water / 66% Methanol, ▲ - Water.

Conditions: Reaction time as indicated, 8.5g solvent, 100 ml autoclave, ambient temperature (20-25°C), 1200rpm, 10mg catalyst, 420 psi  $\text{H}_2/\text{CO}_2$  (a) or 420 psi  $\text{O}_2/\text{CO}_2$  (b).

**Figure 3** –  $\text{H}_2\text{O}_2$  productivity, decomposition and net hydrogenation as a function of solvent composition.

■ – Productivity, ● – Net Hydrogenation, ▲ - Decomposition.

Conditions: 30 min reaction time, 8.5g solvent as indicated, 50 ml autoclave, 20°C, 1200rpm, 10mg catalyst, 420 psi  $\text{H}_2/\text{CO}_2$  + 160 psi  $\text{O}_2/\text{CO}_2$  (productivity), 420 psi  $\text{H}_2/\text{CO}_2$  (hydrogenation) or 420 psi  $\text{O}_2/\text{CO}_2$  (decomposition).

**Figure 4** –  $\text{H}_2\text{O}_2$  productivity, decomposition and net hydrogenation in water as a function of temperature in aqueous solvent.

■ – Productivity, ● – Net Hydrogenation, ▲ - Decomposition.

Conditions: 30 min reaction time, 8.5g  $\text{H}_2\text{O}$  solvent, 50 ml autoclave, temperature as indicated, 1200rpm, 10mg catalyst, 420 psi  $\text{H}_2/\text{CO}_2$  + 160 psi  $\text{O}_2/\text{CO}_2$  (productivity), 420 psi  $\text{H}_2/\text{CO}_2$  (hydrogenation) or 420 psi  $\text{O}_2/\text{CO}_2$  (decomposition).

### Scheme 1


Reaction scheme for the direct synthesis of hydrogen peroxide.



# Figures

Figure 1

a)



b)





Figure 2

a)



b)




Figure 3





Figure 4



Scheme 1

